


Werkstoff Gegenüberstellung



Fittings

ASTM	DIN	Werkstoff-Nr.	EN Standard
C-Stahl			
A234-WPA	St 35.8	1.0305	P235G1TH
A234-WPB	St 45.8	1.0405	
Edelstahl			
A403-WP304	x5CrNi18 10	1.4301	x5CrNi18-10
A403-WP304H	x6CrNi18 11	1.4948	x6CrNi18-10
A403-WP304L	x2SrNi19 11	1.4306	x2CrNi19-11
		1.4841	x15CrNiSi25 -21
A403-WP316	x5CrNiMo 17 122	1.4401	x5CrNiMo17-12-2
A403-WP316 H	x6CrNiMo 17132	1.4919	x6CrNiMo17-12-2
A403-WP316L	x2CrNiMo 17 132	1.4404	x2CrNiMo 17-12-2
A403-WP316Ti	XCrNiMoTi 17 122	1.4571	xCrNiMoTi17-12-2
A403-WP321	x6CrNiTi18-10	1.4541	x6CrNiTi18-10
A403-WP321H	x12CrNiTi18-9	1.4878	x12CrNiTi8-9
A403-WP347	x6CrNiNb18-10	1.4550	x6CrNiNb18-10
NO8904	x1NiCrMoCuN25-20-5	1.4539	904L
S31803	x2CrNiMoN22 5 3	1.4462	DUPLEX
Kaltzäher Stahl			
A420-WPL 3		1.5637	12 Ni 14
A420-WPL6	TTSt35N/V	1.0356	
Warmfester Stahl			
A234-WP1	15Mo3	1.5415	16Mo3
A234-WP5	12CrMo19-5	1.7362	
A234-WP7	x12CrMo7	1.7368	
A234-WP9	x12CrMo9-1	1.7386	
A234-WP11			
A234-WP12	13CrMo44	1.7335	13CrMo4-5
A234-WP22	10CrMo9-10	1.7380	10CrMo9-10
A234-WP91	x10CrMoVNb9-1	1.4903	x10CrMoVNb9-1

mit Sorgfalt, aber ohne Gewähr / Stand November 2007

Tube & Fitting Service GmbH, Lerchenweg 17, 40878 Ratingen
 Tel.: (+49) 02102-16893-0 E-Mail: info@tfs-gmbh.de