


Werkstoff Gegenüberstellung



Flansche

ASTM	DIN	Werkstoff-Nr.	EN Standard
C-Stahl			
A 105	C 21	1.0432	
Edelstahl			
A 182-F304	x5CrNi18 10	1.4301	x5CrNi18-10
A 182-F304H	x6CrNi18 11	1.4948	x6CrNi18-10
A 182-F304L	x2SrNi19 11	1.4306	x2CrNi19-11
A 182-F316	x5CrNiMo 17 122	1.4401	x5CrNiMo17-12-2
A182-F316H	x6CrNiMo 17132	1.4919	x6CrNiMo17-12-2
A182-F316L	x2CrNiMo 17 132	1.4404	x2CrNiMo 17-12-2
A182-F316Ti	XCrNiMoTi 17 122	1.4571	xCrNiMoTi17-12-2
A182-F321	x6CrNiTi18-10	1.4541	x6CrNiTi18-10
A182-F321 H	x12CrNiTi18-9	1.4878	x12CrNiTi8-9
A182-F347	x6CrNiNb18-10	1.4550	x6CrNiNb18-10
A182-F904L	x1NiCrMoCuN25-20-5	1.4539	904L
A182-F51	x2CrNiMoN22 5 3	1.4462	DUPLEX
Kaltzäher Stahl			
A350LF3		1.5637	12 Ni 14
A350-LF2	TStE355	1.0356	P215 NL
Warmfester Stahl			
A182-F1	15Mo3	1.5415	16Mo3
A182-F5	12CrMo19-5	1.7362	
A182-F7	x12CrMo7	1.7368	
A182-F9	x12CrMo9-1	1.7386	
A182-F11			
A182-F12	13CrMo44	1.7335	13CrMo4-5
A182-F22	10CrMo9-10	1.7380	10CrMo9-10
A182-F91	x10CrMoVNb9-1	1.4903	x10CrMoVNb9-1

mit Sorgfalt, aber ohne Gewähr / Stand November 2007

Tube & Fitting Service GmbH, Lerchenweg 17, 40878 Ratingen
 Tel.: (+49) 02102-16893-0 E-Mail: info@tfs-gmbh.de